

SK-5899 SERIES

SK-5899

SILICONE SHEET WITH FIBERGLASS FOR HEAT PRESSING AND FOR SHOCK ABSORPTION

Thickness (mm)	0.5~1.5	ASTM D374
Hardness (Shore A)	75±5	ASTM D2240
Specific Gravity (g/cm ³)	1.2~1.6	ASTM D792
Tensile Strength (kgf/cm ²)	≥75	ASTM D395-03
Elongation (%)	≥150	ASTM D412
Temperature Range (°C)	-40~+250 / +300	-



****Product Color****

Remark: Above test result is from testing laboratory report, for your reference only.

Distributed by:

Universal Part and Service Co.,Ltd.

238 Soi Rangsit - Pathumthani 2

Prachathipat, Thanyaburi

Pathumthani 12130

Tel : 66 (02) 958-1150/Fax : 66 (02) 958-1151