


# KH-1799 SERIES

KH-1799

## SILICONE SHEET

Thickness (mm)	0.1~1.25	ASTMD 374
Hardness (Shore A)	50±5	ASTMD 2240
Specific Gravity (g/cm <sup>3</sup> )	1.12~1.4	ASTMD 729
Tear Strength (kgf/cm <sup>2</sup> )	≥10	ASTMD 624
Elongation (%)	≥200	ASTMD 412
Tensile Strength (kgf/cm <sup>2</sup> )	55	ASTMD 412
Continuous use temp. (°C)	-40~ - 200	-



\*\*\*\*Product Color\*\*\*\*

Remark: Above test result is from testing laboratory report, for your reference only.

**Distributed by:**

Universal Part and Service Co.,Ltd.

238 Soi Rangsit - Pathumthani 2

Prachathipat, Thanyaburi

Pathumthani 12130

Tel : 66 (02) 958-1150/Fax : 66 (02) 958-1151