

UO-5699 SERIES

FLUORINE RUBBER WITH FIBERGLASS REINFORCEMENT

Thickness (mm)	1.0	ASTM D374
Hardness (Shore A)	70±5	ASTM D2240
Specific Gravity (g/cm ³)	1.8	ASTM D792
Tensile Strength (mpa)	9.1	ASTM D395-03
Elongation (%)	180	ASTM D412
Operation Temperature (°C)	-20~+260	-

Remark: Above test result is from testing laboratory report, for your reference only.

Distributed by:

Universal Part and Service Co.,Ltd.

238 Soi Rangsit - Pathumthani 2

Prachathipat, Thanyaburi

Pathumthani 12130

Tel : 66 (02) 958-1150/Fax : 66 (02) 958-1151