

# SK-5899 SERIES

SK-5899-HG8

## ONE SIDE STICKY SILICONE SHEET WITH FIBERGLASS FOR HEAT PRESSING AND FOR SHOCK ABSORPTION

Thickness (mm)	0.4~1.5	ASTM D751
Hardness (Shore A)	50±5	ASTM D2240
Specific Gravity (g/cm <sup>3</sup> )	1.6	ASTM D792
Tensile Strength (kgf/cm <sup>2</sup> )	>120	ASTM D412
Elongation (%)	>10	ASTM D412
Insulation Strength (Volt/mm)	>6000	ASTM D149
Weight Loss (@204 °C/24Hr)	<1	-
Temperature Range (°C)	-60~+180	-
Flammability Level	V-0	UL94



\*\*\*\*Product Color\*\*\*\*

Remark: Above test result is from testing laboratory report, for your reference only.

### Distributed by:

Universal Part and Service Co.,Ltd.

238 Soi Rangsit - Pathumthani 2

Prachathipat, Thanyaburi

Pathumthani 12130

Tel : 66 (02) 958-1150/Fax : 66 (02) 958-1151