


TU-133 SERIES

TU-133YU

THERMAL CONDUCTIVE SILICONE RUBBER GAP FILLER

Thickness (mm)	0.5~18	ASTM D374
Hardness (Shore A)	23/17±3	ASTM D2240
Specific Gravity (g/cm ³)	2.1±0.2	ASTM D792
Tensile Strength (kgf/cm ²)	6.5/26.6±5	ASTM D412
Elongation (%)	0.2/42.7	ASTM D412
Insulation Strength (Volt/mm)	7000	ASTM D149
Temperature Range (°C)	-40~+200	-
Flammability Level	V-0	UL94
Thermal Conductivity (W/m-k)	1.3	ASTM D5470



****Product Color****

Remark: Above test result is from testing laboratory report, for your reference only.

Distributed by:

Universal Part and Service Co.,Ltd.

238 Soi Rangsit - Pathumthani 2

Prachathipat, Thanyaburi

Pathumthani 12130

Tel : 66 (02) 958-1150/Fax : 66 (02) 958-1151