

TU-133 SERIES

TU-133Z

THERMAL CONDUCTIVE SILICONE RUBBER GAP FILLER

Thickness (mm)	0.3~18	ASTM D374
Hardness (Shore A)	35±3	ASTM D2240
Specific Gravity (g/cm ³)	2.3±0.2	ASTM D792
Tensile Strength (kgf/cm ²)	7.8±5	ASTM D412
Elongation (%)	92.3	ASTM D412
Insulation Strength (Volt/mm)	2000	ASTM D149
Temperature Range (°C)	-40~+200	-
Flammability Level	V-0	UL94
Thermal Conductivity (W/m-k)	1.5	ASTM D5470



****Product Color****

Remark: Above test result is from testing laboratory report, for your reference only.

Distributed by:

Universal Part and Service Co.,Ltd.
238 Soi Rangsit - Pathumthani 2
Prachathipat, Thanyaburi
Pathumthani 12130
Tel : 66 (02) 958-1150/Fax : 66 (02) 958-1151